

OK 63.34



OK 63.34 is a rutile MMA-electrode of the 19Cr 12Ni 3Mo-type designed for vertical down welding of steels of similar composition. It provides beads with a very good finish and good tie in profiles to the joint edges.

Classifications	SFA/AWS A5.4 : E316L-16 EN ISO 3581-A : E 19 12 3 L R 1 1 CSA W48 : E316L-16 Werkstoffnummer : 1.4430
Approvals	CWB E316L-16 Seproz UNA 272580 VdTUV 03816

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+, AC
Ferrite Content	FN 3-8
Alloy Type	Austenitic CrNiMo
Coating Type	Acid Rutile

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
ISO			
As Welded	440 MPa	600 MPa	-
AWS			
As Welded	440 MPa	600 MPa	40 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
ISO		
As Welded	20 °C	65 J
As Welded	-120 °C	38 J
AWS		
As Welded	20 °C	65 J
As Welded	-20 °C	52 J

Typical Weld Metal Analysis %

C	Mn	Si	Ni	Cr	Mo	N	Ferrite FN
0.02	0.8	0.8	11.8	18.7	2.8	0.13	6

Deposition Data

Diameter	Current	Voltage	Number of electrodes/ kg weld metal	Fusion time per electrode at 90% I max	Deposition Efficiency %	Deposition Rate @ 90% I max
2.5 x 300.0 mm	70-90 A	22 V	94	39 sec	70 %	1.0 kg/h
3.2 x 300.0 mm	80-130 A	25 V	59	39 sec	70 %	1.6 kg/h