

OK Autrod NiCrMo-3

A continuous solid corrosion and heat-resisting Ni-Cr-Mo wire for welding of high alloyed heat-resisting and corrosion resisting materials, 9%Ni-steels and similar steels with high notch toughness at low temperatures. Also for joining of dissimilar metals of the types mentioned. The weld metal has very good mechanical properties at high and low temperatures. Good resistance to pitting and stress corrosion. This alloy is extensively required for weld cladding of valve components and pipe inner diameters in oil and gas applications.

Classifications Wire Electrode	SFA/AWS A5.14 : ERNiCrMo-3 EN ISO 18274 : S Ni 6625
Approvals	CE EN 13479 DNV-GL 1.2 mm NAKS/HAKC 1.0-1.2 mm VdTUV 12413

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Alloyed nickel (Ni + 22 % Cr + 9 % Mo - 3.5 % Nb)
Shielding Gas	I1, I3, M12 (EN ISO 14175)

Typical Wire Composition %

C	Mn	Si	Ni	Cr	Mo	Fe	Nb+Ta
0.02	0.04	0.06	bal	22.7	8.6	0.3	3.5

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
0.9 mm (0.035 in.)	80-190 A	20-27 V	5.0-16.0 m/min (197-630 in./min)	2.0-4.2 kg/h (4.4-9.3 lb/h)
1.0 mm (0.040 in.)	100-200 A	21-27 V	6.0-13.0 m/min (236-512 in./min)	2.5-5.5 kg/h (5.5-12. lb/h)
1.14 mm (0.045 in.)	130-240 A	22-28 V	6.0-12.0 m/min (236-472 in./min)	3.0-5.7 kg/h (6.6-12. lb/h)
1.2 mm (0.047 in.)	160-280 A	24-30 V	6.0-10.0 m/min (236-394 in./min)	3.6-6.0 kg/h (7.9-13. lb/h)
1.6 mm (1/16 in.)	200-350 A	25-32 V	4.0-8.0 m/min (157-315 in./min)	4.3-8.6 kg/h (9.5-19. lb/h)