

## Purus 42 CF

A non copper coated, G3Si1/ER70S-6 solid wire for GMAW of carbon-manganese steels. Purus 42 CF is particularly suited to be used in general construction, automotive components and mobile machinery industries. The wire may be welded with either a gas mixture or with pure CO<sub>2</sub> as the shielding gas. Purus 42 CF is designed to give a clean weld bead with a minimum of silica islands, low fumes and extremely low spatter levels. The wire is suitable for robotic applications at high deposition rates.

<b>Classifications Weld Metal</b>	EN ISO 14341-A : G 38 3 C1 3Si1 EN ISO 14341-A : G 42 4 M20 3Si1 EN ISO 14341-A : G 42 4 M21 3Si1
<b>Classifications Wire Electrode</b>	SFA/AWS A5.18 : ER70S-6 EN ISO 14341-A : G 3Si1
<b>Approvals</b>	CE EN 13479 CWB B-G 49A 3 C1 S6 (B-G 49A 3 C G6) DB 42.039.44 VdTUV 19260

Approvals are based on factory location. Please contact ESAB for more information.

<b>Alloy Type</b>	Carbon-manganese steel (Mn/Si-alloyed)
<b>Shielding Gas</b>	M20, M21, C1 (EN ISO 14175)

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>EN 80Ar 20CO<sub>2</sub></b>			
As Welded	470 MPa	560 MPa	25 %
<b>EN CO<sub>2</sub></b>			
As Welded	430 MPa	530 MPa	24 %
<b>AWS CO<sub>2</sub></b>			
As Welded	420 MPa	530 MPa	30 %
<b>EN 92Ar 8CO<sub>2</sub></b>			
As Welded	475 MPa	570 MPa	26 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>AWS CO<sub>2</sub></b>		
As Welded	-30 °C	80 J
<b>EN 80Ar 20CO<sub>2</sub></b>		
As Welded	20 °C	130 J
As Welded	-30 °C	90 J
As Welded	-40 °C	80 J
<b>EN CO<sub>2</sub></b>		
As Welded	20 °C	110 J
As Welded	-30 °C	75 J
As Welded	-40 °C	65 J
<b>EN 92Ar 8CO<sub>2</sub></b>		
As Welded	20 °C	150 J
As Welded	-30 °C	100 J
As Welded	-40 °C	75 J

### Typical Wire Composition %

C	Mn	Si
0.08	1.45	0.85

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
0.8 mm	60-200 A	18-24 V	3.2-10.0 m/min	0.8-2.3 kg/h
0.9 mm	70-250 A	18-26 V	3.0-12.0 m/min	0.9-3.5 kg/h
1.0 mm	80-300 A	18-32 V	2.7-15.0 m/min	1.0-5.5 kg/h
1.14 mm	100-350 A	18-34 V	2.6-15.0 m/min	1.2-7.0 kg/h
1.2 mm	120-380 A	18-35 V	2.5-15.0 m/min	1.3-8.0 kg/h
1.32 mm	130-400 A	19-35 V	2.4-15.0 m/min	1.5-8.5 kg/h
1.4 mm	150-420 A	22-36 V	2.3-12.0 m/min	1.6-8.7 kg/h



## Purus 42 CF

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.6 mm	225-550 A	28-38 V	2.3-10.0 m/min	2.1-9.4 kg/h

Approvals are based on factory location. Please contact ESAB for more information.